



PRODUCT DATA

3701

HI-HEAT SILICONE
ALUMINUM

Description: designed for use on steel subject to elevated temperatures. Recommended use is two coats applied directly to the properly prepared steel.

Dry Temperature Limits: To 1200 Deg. F.- Intermittent
To 800-1000 Deg. F. (538 Deg. C.) - Sustained

Surface Preparation Carbon steel surfaces must be dry and cleaned of dirt, oils, rust and other contaminants. For best performance and service, the most desirable preparation is abrasive blast cleaning to Near-White, SSPC-SP-10 (Swedish Std. SA 2 1/2.) Stainless steel surfaces (for coating with 3711) should be given a sweep-blast, or otherwise mechanically abraded sufficiently to create a surface angularity which will give improved bonding.

Application Equipment: Brush, Roller, Airless or Conventional spray. To obtain maximum edge protection and film build, spray application is recommended.

Application Conditions:

- Noncontaminated surface, free of all oil, grease, mildew, other contamination
- Dry, dust-free metal surface
- Metal temperature above 60 deg.F
- Metal temperature at least 5 deg. above the dew point
- Ambient temperature above 50 deg.F
- Humidity less than 90%
- Material temperature between 60 and 90 deg.F

Primer: 1312 or self prime

Thinner: T-33

Clean Up Solvent: T-33

Safe Application Conditions: Consult MSDS for proper handling, cleanup, disposal, and use of personal protective equipment. Circulate sufficient air to maintain working environment below the PEL and LEL. Apply according to local, state, and federal (OSHA) regulations.

Finish: Medium Gloss

Color: aluminum

Volume Solids: 30%

VOC:

Flash Point: 95 deg F - 35 deg C

Dry Film Thickness: 1.0-1.5

Wet Film Thickness: 3.0-5.0

Theoretical Coverage: 610 per mil DFT

Shelf Life Time: 12 months

Dry Time:

To Touch - 4 hours Recoat - after a minimum of 24 hours Attains full hardness only after heat exposure above 300 Deg. F.

120 Tremon Street, Gordon Georgia, 31031 800.659-0908 fax no. 478.628.5870 Web- elitedot.com

Seller's liability (or damages arising out of breach of warranty or negligence is expressly limited to the purchase price of the products delivered hereunder. All technical advice, recommendations and services rendered by the Seller gratis, they are based on technical data which the Seller believes to be reliable, and are intended for use by persons having skill and know how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations technical advice or services are not to be taken as license to operate under or intended to suggest infringement or any existing patent.