



PRODUCT DATA

7510

Aluminum Epoxy Mastic

Description: A two component, DTM mastic coating designed to permit application to rusty steel. For use in areas where higher performance is needed than can be obtained with conventional coatings, and only hand or power tool cleaning can be performed. Recommended for touchup and protection of weathered aluminum or hot-dipped galvanizing. May be topcoated with epoxy or urethane coatings up to 60 days after application. High volume solids and low VOC.

Typical Uses: For use as a maintenance coating over existing alkyd, epoxy, and zinc rich coatings, which are in sound condition and tightly adherent to the substrate. Useful for the protection of structural steel, piping, bridges, tank exteriors, equipment and other surfaces exposed to corrosive atmospheric or industrial environments.

Dry Temperature Limits: up 200 deg.F

Surface Preparation: Surfaces should be clean and dry. Remove all oil, grease, mildew or other contamination by solvent or detergent cleaning or other effective means.

Application Equipment: Brush, roller, airless or conventional spray. To obtain maximum edge protection and film build, spray application is recommended.

Application Conditions:

- Noncontaminated surface, free of all oil, grease, mildew, other contamination
- Dry, dust-free metal surface
- Metal temperature above 60 deg.F
- Metal temperature at least 5 deg. above the dew point
- Ambient temperature above 50 deg.F
- Humidity less than 90%
- Material temperature between 70 and 90 deg.F

Primer: n/a, self-prime

Thinner: T-33

Clean Up Solvent: T-33

Safe Application Conditions: Consult MSDS for proper handling, cleanup, disposal, and use of personal protective equipment. Circulate sufficient air to maintain working environment below the PEL and LEL. Apply according to local, state, and federal (OSHA) regulations.

Finish: low sheen

Color: metallic gray

Volume Solids: 91 +/- 1.0% (mixed)

VOC: 0.76 lbs./gal. (mixed)

Flash Point: 105 deg.F

Mixing Ratio: 1:1 by volume

Dry Film Thickness: 5 to 7 mils

Wet Film Thickness: 6 to 8 mils

Theoretical Coverage: 1460 sq.ft./gal.@ 1 mils

Induction Time: none

Pot Life Time: 5 hours @ 75 deg.F

Shelf Life Time: 12 months +

Dry Time: @ 77 deg.F (25 deg.C)

Dry to Touch 4 hours

Dry Tack-free 12 hours

Dry to Recoat 24 hours

120 Tremon Street, Gordon Georgia, 31031 800.659.0908 fax no. 478.628.5870

Seller's liability (or damages arising out of breach of warranty or negligence is expressly limited to the purchase price of the products delivered hereunder. All technical advice, recommendations and services rendered by the Seller gratis, they are based on technical data which the Seller believes to be reliable, and are intended for use by persons having skill and know how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations technical advice or services are not to be taken as a license to operate under or intended to suggest infringement or any existing patent.