



## PRODUCT DATA

### Micaceous Iron Oxide

G502 #26373 Gray Topcoat  
G506 #22247 Green Topcoat  
G509 #226307 Gray Topcoat  
G518 Aluminum Topcoat  
G540 #24441 Green tipcoat

**Description:** A high build alkyd topcoat using micaceous iron oxide pigment. Applies more film in one coat than most other alkyd coatings. Meets requirements of Virginia Dept. of Highways Section 239.10: Number 8 Micaceous Iron Oxide Intermediate Coat.

**Typical Uses:** For industrial and commercial use for the protection of structural steel, tank exteriors, bridges and other surfaces exposed to corrosive environments. Use as a high build alkyd intermediate coat over properly primed and prepared ferrous metal surfaces.

**Special Qualifications:** SSPC Paint No. 25, Virginia DOT System no. 1, West Virginia DOT System 711.8.2.

**Dry Temperature Limits:** 250 deg.F

**Surface Preparation:** Surfaces should be clean and dry. Remove all oil, grease, mildew or other contamination by solvent or detergent cleaning or other effective means.

**Thinner:** T-160 Thinner

**Mixing:** Stir thoroughly prior to use.

**Application Equipment:** brush, roller, or airless spray using a minimum 30:1 ratio pump with 0.017 (617) to 0.019 (619) inch diameter orifice for airless spray gun tip at a 2,400 psi recommended minimum fluid pressure at tip to obtain proper atomization. An artist brush can be used for touchup of WFT marks and other small repair areas.

**Application Conditions:**

- Noncontaminated profile (pretreat and blast contaminated surfaces)
- Dry, dust-free metal surface
- Metal temperature above 40 deg.F
- Metal temperature at least 5 deg. above the dew point
- Ambient temperature above 40 deg.F
- Humidity less than 90%
- Material temperature between 40 and 90 deg.F

**Safe Application Conditions:** Consult MSDS for proper handling, cleanup, disposal, and use of personal protective equipment. Circulate sufficient air to maintain working environment below the PEL and LEL. Apply according to local, state, and federal (OSHA) regulations.

**Finish:** flat

**Color:** Range of

**Volume Solids:** 50.5% ± 2%

**VOC:** EPA Test Method 24 - 3.20 Pounds/Gal

**Flash Point:** 105 deg.F

**Dry Film Thickness:** 2.5 mils (64 microns)  
D.F.T

**Wet Film Thickness:** 5 mils (127 microns)  
wet

**Theoretical Coverage:** Per Gallon @1 mil  
(25 microns) D.F.T. - 811 ft.<sup>2</sup>

**Dry Time:** To touch- 5 Hours To recoat- 24  
Hours

120 Tremon Street, Gordon Georgia, 31031 800.659-0908 fax no. 478.628.5870 elitedot.com

Seller's liability (or damages arising out of breach of warranty or negligence is expressly limited to the purchase price of the products delivered hereunder. All technical advice, recommendations and services rendered by the Seller gratis, they are based on technical data which the Seller believes to be reliable, and are intended for use by persons having skill and know how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations technical advice or services are not to be taken as license to operate under or intended to suggest infringement or any existing patent.