



## PRODUCT DATA

# W-400

## Latex Blockfiller

**Description:** Latex Block Filler is intended for the filling and smoothing of open textured masonry surfaces, such as concrete block, cinder block, concrete, and similar surfaces, prior to finish coating. Interior, it aids appearance and provides for easier cleaning. Exterior, by filling the surface voids, it prevents penetration by rain. Elite Alkyd, Latex, and Elite Chem coatings may be used for topcoats. Situations where there is moisture seepage into the block, or where there is moisture movement through the wall to the coated side creates difficult to coat surfaces. The use of W-400 is not recommended in these cases.

**Dry Temperature Limits:** 190 Deg. F. (88 Deg. C.)

**Surface Preparation:** All surfaces to be coated must be dry, cleaned free of dust, dirt, rust, oils, and other contaminants

**Application Equipment:** Brush, Roller, Airless or Conventional spray. To obtain maximum edge protection and film build, spray application is recommended.

**Application Conditions:**

- Noncontaminated surface, free of all oil, grease, mildew, other contamination
- Dry, dust-free metal surface
- Metal temperature above 60 deg.F
- Metal temperature at least 5 deg. above the dew point
- Ambient temperature above 50 deg.F
- Humidity less than 90%
- Material temperature between 60 and 90 deg.F

**Primer:** *n/a*

**Thinner:** water

**Clean Up Solvent:** water

**Safe Application Conditions:** Consult MSDS for proper handling, cleanup, disposal, and use of personal protective equipment. Circulate sufficient air to maintain working environment below the PEL and LEL. Apply according to local, state, and federal (OSHA) regulations.

**Finish:** Flat

**Color:** White

**Volume Solids:** 43%

**VOC:** 159 lbs./gal. (189 g/l)

**Flash Point:** *non flammable*

**Dry Film Thickness:** Sufficient to fill block surface

**Wet Film Thickness:**

**Theoretical Coverage:** 50-150 square feet per gallon. The actual coverage will be less, depending on application technique, job conditions, and type of surface to be coated.

**Shelf Life Time:** 12 months

**Dry Time:** ~~To Touch-~~ 1 hour ~~Recoat-~~ after 4 hours with Latex Paints; allow 16 hours before recoating with solvent base coatings.

120 Tremon Street, Gordon Georgia, 31031 800.659-0908 fax no. 478.628.5870 Web- [elitedot.com](http://elitedot.com)

Seller's liability (or damages arising out of breach of warranty or negligence is expressly limited to the purchase price of the products delivered hereunder. All technical advice, recommendations and services rendered by the Seller gratis, they are based on technical data which the Seller believes to be reliable, and are intended for use by persons having skill and know how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations technical advice or services are not to be taken as license to operate under or intended to suggest infringement or any existing patent.